

BEST AVAILABLE COPY  
BEST AVAILABLE COPY  
BEST AVAILABLE COPY

DERWENT-ACC-NO: 1993-083468

DERWENT-WEEK: 199310

COPYRIGHT 2005 DERWENT INFORMATION LTD

TITLE: Artificial fur - has two layered pile  
structure with longer hollow irregular fibres and shorter  
round or trilobal fibres which are tufted at a defined  
density

INVENTOR: HONG, S; KANG, T

PATENT-ASSIGNEE: KOLON CO[KOLON]

PRIORITY-DATA: 1990KR-0002936 (March 6, 1990)

PATENT-FAMILY:

PUB-NO	PUB-DATE	LANGUAGE
PAGES MAIN-IPC		
KR 9206129 B	July 31, 1992	N/A
000 D06N 007/04		

APPLICATION-DATA:

PUB-NO	APPL-DESCRIPTOR	APPL-NO
APPL-DATE		
KR 9206129B	N/A	1990KR-0002936
March 6, 1990		

INT-CL (IPC): D06N007/04

ABSTRACTED-PUB-NO: KR 9206129B

BASIC-ABSTRACT:

An artificial fur has a two-layered pile structure consisting of longer fibre and shorter. Length and fineness of the longer fibre are 30-80 mm and 10-60 denier, respectively, while those of the shorter fibre are 20-60 mm and 1-10 denier. The cross-section of the longer is hollow or irregular yarn, and that of the shorter is circular or trilobal yarn. After folding, twisting and tufting the longer and the shorter fibre, density of warp and weft of

the  
longer is 100-400 ends per inch, while that of the shorter is 5,000-  
15,000 ends  
per inch. The fibre may be polyester, nylon, acryl and polybutylene  
terephthalate. The longer fibre is pref. polybutylene terephthalate  
and the  
shorter are acryl or polyester.

TITLE-TERMS: ARTIFICIAL FUR TWO LAYER PILE STRUCTURE LONG HOLLOW  
IRREGULAR


FIBRE SHORT ROUND TRILOBAL FIBRE TUFT DEFINE DENSITY

DERWENT-CLASS: A14 A23 F05

CPI-CODES: A11-C05A; A12-S05J; F01-E02; F01-E03; F02-D; F04-B03;

SECONDARY-ACC-NO:


CPI Secondary Accession Numbers: C1993-037049




Photocopies of three Known Prior Art Carpet Samples  
collected by Examiner prior to July 3, 2003.

A handwritten signature in black ink, consisting of a series of loops and a long horizontal stroke extending to the right.

10.01.05







**This Page is Inserted by IFW Indexing and Scanning  
Operations and is not part of the Official Record**

**BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☒ FADED TEXT OR DRAWING
- ☒ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☒ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: \_\_\_\_\_

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.**